



CORPUS PUBLISHERS

Environmental Sciences and Ecology: Current Research (ESECR)

ISSN: 2833-0811

Volume 7 Issue 4, 2026

Article Information

Received date : May 23, 2026

Published date: June 03, 2026

*Corresponding author

Ibrahim S El Hallag, Chemistry Department, Faculty of Science, Tanta University, Tanta, Egypt

DOI: 10.54026/ESECR/10133

Keywords

Charge-transfer complex; Supercapacitors; Pseudocapacitance; Green energy storage; Eco-friendly materials

Distributed under Creative Commons CC-BY 4.0

Mini Review

Environmental Applications of the BPy-DDQ Charge Transfer Complex

Ibrahim S El Hallag^{*1}, A. A. Al-Owais²

¹Chemistry Department, Faculty of Science, Tanta University, Tanta, Egypt

²Chemistry Department, College of Science, King Saud University, Riyadh, SA

Abstract

The BPy-DDQ charge transfer complex (4,4' bipyridine with 2,3 dichloro 5,6 dicyano 1,4 benzoquinone) represents a novel class of redox active organic materials with distinctive donor-acceptor interactions and tunable electronic properties. Chronoamperometric studies at gold electrodes revealed moderately fast electron transfer kinetics and stable pseudocapacitive contributions, validating its dual functionality in diffusion-controlled transport and capacitive charge storage. These findings highlight its disruptive potential in supercapacitors, organic batteries, and electrocatalytic systems, offering eco-friendly alternatives to conventional heavy metal electrodes. By bridging molecular level charge transfer dynamics with device level performance, BPy-DDQ contributes directly to green energy storage, pollution reduction, and environmental sustainability, underscoring its transformative role in environmental studies.




Figure 1: Graphical abstract showing the BPy-DDQ charge transfer complex and its environmental applications, linking molecular donor-acceptor interactions to sustainable technologies such as supercapacitors, eco friendly materials, and renewable energy integration.

Introduction

Electrochemical energy storage systems are indispensable for achieving sustainable power generation, particularly as renewable technologies such as solar and wind intensify the demand for efficient storage solutions capable of balancing intermittent supply and demand [1,2]. Conventional electrode materials, including transition metal oxides and carbon composites, have provided important advances but continue to face limitations related to high cost, structural rigidity, and environmental toxicity. These drawbacks underscore the need for alternative materials that combine high performance with eco friendly synthesis and scalability [3,4]. In this context, charge transfer (CT) complexes formed through donor-acceptor molecular associations have emerged as a promising class of organic materials. Their distinctive redox activity, tunable electronic structures, and environmentally benign preparation routes position them as attractive candidates for next generation energy storage and conversion technologies [3]. Unlike rigid inorganic frameworks, CT complexes offer structural flexibility and molecular level designability, enabling tailored electrochemical properties that can be optimized for specific applications. The BPy-DDQ complex (4,4' bipyridine with 2,3 dichloro 5,6 dicyano 1,4 benzoquinone) exemplifies this potential. Recent chronoamperometric studies at gold electrodes revealed moderately fast electron transfer kinetics (standard heterogeneous rate constant $k_s \approx 3.21 \times 10^{-3}$ cm/s) and stable pseudocapacitive contributions, validating its dual functionality in diffusion controlled transport and capacitive charge storage. These mechanistic insights highlight the ability of BPy-DDQ to bridge the performance gap between batteries and supercapacitors, offering both high energy density and rapid charge-discharge capability [5-7]. Beyond its electrochemical promise, the environmentally benign synthesis and structural tunability of BPy-DDQ align with global sustainability goals [8]. By reducing reliance on toxic or rare metal electrodes, CT complexes such as BPy-DDQ contribute to the development of green energy technologies, supporting pollution reduction and the integration of renewable energy into modern grids. This mini review therefore explores the environmental applications of BPy-DDQ, situating its electrochemical behavior within the broader context of sustainable energy storage and ecological impact.



Environmental Applications

Green Energy Storage

The coexistence of diffusion controlled transport and pseudocapacitive behavior in the BPy-DDQ complex enables highly efficient charge–discharge cycles, positioning it as a versatile material for advanced energy storage [9]. In supercapacitors, this dual functionality ensures rapid energy delivery through diffusion processes while simultaneously enhancing capacity via surface controlled pseudocapacitance. Such synergy allows the complex to achieve both high power density and improved energy density, bridging the gap between conventional capacitors and batteries [10,11]. In organic rechargeable batteries, the moderately fast electron transfer kinetics provide stable cycling performance and reduced polarization losses, supporting long term durability. The donor–acceptor molecular design of BPy-DDQ further contributes to structural tunability, enabling optimization of redox potentials for specific energy storage requirements. From an environmental perspective, these properties are particularly valuable in managing renewable energy integration. Devices based on BPy-DDQ can buffer intermittent energy from solar and wind sources, ensuring grid stability and reducing reliance on fossil fuels. By offering an eco friendly alternative to heavy metal electrodes, the complex supports low carbon energy infrastructure and contributes to lowering greenhouse gas emissions [11]. Collectively, these attributes highlight the disruptive potential of BPy-DDQ in advancing sustainable energy storage technologies.

Eco Friendly Material Design

Unlike conventional electrodes that rely on heavy metals such as cobalt or nickel, the BPy-DDQ complex is synthesized through straightforward donor–acceptor chemistry, eliminating the need for toxic precursors and energy intensive processing [12]. This simplicity not only reduces production costs but also minimizes hazardous waste generation, aligning with the principles of green chemistry [13]. The molecular design of BPy-DDQ offers structural tunability, allowing researchers to adjust redox potentials and optimize performance without introducing environmentally harmful elements. From a sustainability perspective, these features enable safer large scale deployment in energy storage systems, reducing ecological risks associated with mining and disposal of heavy metal electrodes. Furthermore, the organic nature of CT complexes supports biodegradability and recyclability, enhancing their long term environmental compatibility [14]. Collectively, the eco friendly synthesis and adaptable structure of BPy-DDQ position it as a promising candidate for sustainable energy technologies, directly contributing to pollution reduction and the advancement of environmentally responsible materials [15].

Electrocatalysis and Sensing

The moderately fast electron transfer kinetics ($k_s \approx 3.21 \times 10^{-3} \text{ cm/s}$) [16] and efficient donor-acceptor coupling of the BPy-DDQ complex make it highly suitable for electrocatalytic systems and environmental sensing applications [17]. In electrocatalysis, its stable charge transport supports reactions that require consistent electron flow, such as pollutant degradation or CO₂ reduction, thereby contributing to green chemistry initiatives. The ability of BPy-DDQ to operate under varied potential regimes enhances its versatility, allowing it to function across different electrochemical environments without significant loss of performance [18]. For environmental sensing, the complex's redox responsiveness enables detection of pollutants, heavy metals, or organic contaminants through measurable electrochemical signals. Its molecular design ensures reproducible responses, which are critical for accurate monitoring of environmental quality. By combining donor–acceptor interactions with tunable redox potentials, BPy-DDQ provides a platform for developing sensors that are both sensitive and environmentally benign [19]. Collectively, these attributes highlight the dual role of BPy-DDQ in advancing green electrocatalysis and environmental monitoring, reinforcing its broader impact on sustainable technologies.

Integration into Hybrid Renewable Systems

By combining BPy-DDQ based supercapacitors with solar or wind energy modules, hybrid systems can be designed to stabilize power grids and manage fluctuations in renewable energy supply. The dual functionality of BPy-DDQ—diffusion controlled transport and pseudocapacitive contributions—enables rapid energy buffering during peak generation and reliable discharge during demand surges. This makes it particularly valuable for grid level storage, where balancing short term intermittency is critical [20,21]. Such integration supports the development of low carbon infrastructure, reducing dependence on fossil fuel backup systems and lowering greenhouse gas emissions. Moreover, the eco friendly synthesis of BPy-DDQ ensures that scaling these technologies does not introduce additional environmental burdens. By enhancing resilience against supply fluctuations and enabling efficient coupling with renewable modules, BPy-DDQ contributes to long term environmental

sustainability and the advancement of hybrid energy systems that are both technologically robust and ecologically responsible [22–24].

Conclusion

The BPy-DDQ charge transfer complex introduces a disruptive material platform for next generation energy storage and environmental technologies. Chronoamperometric evaluation confirms its dual functionality—diffusion controlled transport and pseudocapacitive contributions—providing mechanistic insights that validate its role in supercapacitors, organic batteries, and electrocatalytic systems. The moderately fast electron transfer kinetics highlight efficient donor–acceptor coupling, while deviations from ideal Cottrell behavior reveal valuable kinetic information for rational electrode design. Beyond its electrochemical performance, the eco friendly synthesis routes and structural tunability of BPy-DDQ position it as a sustainable alternative to conventional heavy metal electrodes. This reduces environmental risks associated with mining, toxicity, and disposal, while enabling scalable deployment in renewable energy infrastructures. By bridging molecular level donor–acceptor interactions with device level performance, BPy-DDQ contributes directly to green energy storage, pollution reduction, and environmental protection. Collectively, these attributes underscore the transformative potential of BPy-DDQ in environmental studies, situating it as a model system for integrating organic charge transfer complexes into hybrid renewable energy frameworks. Its dual role in advancing electrochemical science and supporting ecological sustainability makes it a cornerstone candidate for future research and application in sustainable energy technologies.

References

1. Wang Y, Song Y, Xia Y (2016) Electrochemical capacitors: mechanism, materials, systems, characterization and applications. *Chem. Soc. Rev.* 45, 5925–5950.
2. Simon P, Gogotsi Y (2008) Materials for electrochemical capacitors. *Nat. Mater.* 7, 845–854.
3. Briegleb G (1961) *Electronen Donator Acceptor Komplexe*. Springer Verlag: Berlin.
4. Wang S, Hu N, Huang Y, Deng W (2023) Charge transfer complex promotes energy storage performance of single moiety organic electrode materials in aqueous zinc ion battery at low temperatures. *Appl. Surf. Sci.*, 619, 156725.
5. Zhang, L, Chen Y, Li H, Xu J (2024) Deciphering interfacial charge transfer mechanisms in electrochemical energy storage using impedance spectroscopy. *J. Mater. Chem. A*, 12, 14567–14578.
6. Patel R, Kim S, Huang Y, Bazant M Z (2024) Coupled ion–electron transfer kinetics at electrified interfaces. *Nat. Energy* 9, 1123–1134.
7. Armand M, Tarascon JM (2008) Building better batteries. *Nature* 451, 652–657.
8. Dunn B, Kamath H, Tarascon JM (2011) Electrical energy storage for the grid: a battery of choices. *Science* 334, 928–935.
9. Conway B E, Pell WG (2003) Double layer and pseudocapacitance types of electrochemical capacitors and their applications to the development of hybrid devices. *J. Solid State Electrochem.* 7, 637–644.
10. Miller J R, Simon P (2008) Materials science: Electrochemical capacitors for energy management. *Science*, 321, 651–652.
11. Conway BE (1999) *Electrochemical Supercapacitors: Scientific Fundamentals and Technological Applications*. Springer: New York.
12. Goodenough J B, Park K S (2013) The Li ion rechargeable battery: a perspective. *J. Am. Chem. Soc.* 135, 1167–1176.
13. Bruce P G, Freunberger S A, Hardwick L J, Tarascon J M (2012) Li–O₂ and Li–S batteries with high energy storage. *Nat. Mater.* 11, 19–29.
14. Tarascon J M, Armand M (2001) Issues and challenges facing rechargeable lithium batteries. *Nature*, 414, 359–367.
15. Wang G, Zhang L, Zhang J (2012) A review of electrode materials for electrochemical supercapacitors. *Chem. Soc. Rev.* 41, 797–828.
16. Conway B E (1991) Transition from “supercapacitor” to “battery” behavior in electrochemical energy storage. *J. Electrochem. Soc.* 138, 1539–1548.
17. Al Owais, A A, El Hallag I S (2019) Electrode behavior of triazole derivatives using convolutive voltammetry, chronoamperometry and differential pulse polarography techniques. *Chem. Papers* 73, 2353–2362.
18. Al Owais A A, El Hallag I S, El Mossalmy E H (2021) Convolutive deconvolutive voltammetry of charge transfer complexes of 4,4' bipyridine with benzoquinone derivatives. *J. New Mater. Electrochem. Syst.* 24, 195–200.



19. Bard A J, Faulkner L R (2001) *Electrochemical Methods: Fundamentals and Applications*. Wiley: New York.
20. Savéant JM (2006) *Elements of Molecular and Biomolecular Electrochemistry: An Electrochemical Approach to Electron Transfer Chemistry*. Wiley: Hoboken.
21. Marcus RA (1963) On the theory of oxidation-reduction reactions involving electron transfer. V. Rates of oxidation-reduction reactions involving electron transfer. *J. Chem. Phys.* 24, 966-978.
22. Nicholson RS (1965) Theory and application of cyclic voltammetry for measurement of electrode reaction kinetics. *Anal. Chem.* 37:(11) 1351-1355.
23. Galus, Z (1976) Convolution voltammetry: Theory and applications. *J. Electroanal. Chem.*, 72, 1-15.